

锂电池 UN38.3 测试报告
Lithium Battery UN38.3 Test Report

Sample Name	Li-Polymer Battery 903040
Client	HIGHER POWER TECHNOLOGY CO.,LIMITED
Manufacturer	HIGHER POWER TECHNOLOGY CO.,LIMITED

HIGHER POWER TECHNOLOGY CO.,LIMITED

I、SAMPLE DESCRIPTION

Sample Name	Li-Polymer Battery		Battery Type	903040	
Client	HIGHER POWER TECHNOLOGY CO.,LIMITED				
Manufacturer	HIGHER POWER TECHNOLOGY CO.,LIMITED				
Nominal Voltage	3.7V	Rated Capacity	1200 mAh	Limited Charge Voltage	4.2V
Charge Current	1200 mA	Maximum Continuous Charge Current	1200 mA	End Charge Current	12 mA
Cut-off Voltage	3.0V	Maximum Discharge Current	1200 mA	Use	---
Cells Number	1PCS	Cell Model	903040	Rated Capacity	1200 mAh
Manufacturer of cell		HIGHER POWER TECHNOLOGY CO.,LIMITED			
Chemical component		LiCoO ₂ , C			
Client date	2015-01-16		Finished date	2015-02-25	

II、STANDARD

United Nations Recommendations On The Transport Of Dangerous Goods, Manual Of Tests And Criteria.

III、TEST ITEM

- | | |
|------------------------|---------------------------|
| 1. Altitude simulation | 5. External short circuit |
| 2. Thermal test | 6. Crush |
| 3. Vibration | 7. Overcharge |
| 4. Shock | 8. Forced discharge |

IV、CONCLUSION

ITEM	SAMPLE NUMBER	STANDARD	CONCLUSION
Altitude simulation	N1~N4 C1~C4	UN38.3	PASS
Thermal test			PASS
Vibration			PASS
Shock			PASS
External short circuit			PASS
Crush	N9~N13		PASS
Overcharge	N5~N8 C5~C8		PASS
Forced discharge	---		N/A (Not applicable)

The submitted battery and component cell were complied with the stated requirements of UN38.3.

Notes:

N1~N8: Batteries at first cycle, in fully charged states;

N9~N13: Component cells of rechargeable batteries, at first cycle at 50% of the design rated capacity;

C1~C8: Batteries, after 50 cycles ending in fully charged states.

V、 PHOTO OF THE SAMPLE



Authenticate the photo on original report only

VI、 TEST METHOD

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells or batteries. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

In order to quantify the mass loss, the following procedure is provided:

$$\text{Mass loss}(\%) = (M_1 - M_2) / M_1 \times 100$$

Where M_1 is the mass before the test and M_2 is the mass after the test. When mass loss does not exceed the values in Table blow, it shall be considered as “no mass loss”.

Mass M of cell or battery	Mass loss limit
$M < 1\text{g}$	0.5%
$1\text{g} \leq M \leq 75\text{g}$	0.2%
$M > 75\text{g}$	0.1%

T.1 Altitude simulation

Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature ($20 \pm 5^\circ\text{C}$).

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.2 Thermal test

Test cells and batteries are to be stored for at least six hours at a test temperature equal to $72 \pm 2^\circ\text{C}$, followed by storage for at least six hours at a test temperature equal to $-40 \pm 2^\circ\text{C}$. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature ($20 \pm 5^\circ\text{C}$). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.3 Vibration

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.

The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).

For cells and small batteries: from 7 Hz a peak acceleration of 1 g_n is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 g_n occurs (approximately 50 Hz).

A peak acceleration of 8 g_n is then maintained until the frequency is increased to 200 Hz.

For large batteries: from 7 Hz to a peak acceleration of 1 g_n is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 g_n occurs (approximately 25 Hz). A peak acceleration of 2 g_n is then maintained until the frequency is increased to 200 Hz.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.4 Shock

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each cell or battery shall be subjected to a half-sine shock of peak acceleration of 150 g_n and pulse duration of 6 milliseconds. Each cell or battery shall be subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

However, large cells and large batteries shall be subjected to a half-sine shock of peak acceleration of 50 g_n and pulse duration of 11 milliseconds. Each cell or battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of each of three mutually perpendicular mounting positions of the cell for a total of 18 shocks.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.5 External short circuit

The cell or battery to be tested shall be temperature stabilized so that its external case temperature reaches 55 ± 2 °C and then the cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at 55 ± 2 °C. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 55 ± 2 °C.

Cells and batteries meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

T.6 Impact / Crush

Impact (applicable to cylindrical cells greater than 20 mm in diameter)

The sample cell or component cell is to be placed on a flat smooth surface. A $15.8 \text{ mm} \pm 0.1 \text{ mm}$ diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A $9.1 \text{ kg} \pm 0.1 \text{ kg}$ mass is to be dropped from a height of $61 \pm 2.5 \text{ cm}$ at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the $15.8 \text{ mm} \pm 0.1 \text{ mm}$ diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.

Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells not more than 20 mm in diameter)

A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches $13 \text{ kN} \pm 0.78 \text{ kN}$;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.

Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.

Cells and component cells meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly and no fire during the test and within six hours after this test.

T.7 Overcharge

The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature; the duration of the test shall be 24 hours.

Rechargeable batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.


T.8 Forced discharge

Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

VII、 TEST PROCEDURE



VIII、 MAIN TEST APPARATUS

SZSB-121 Rechargeable battery test system
SZSB-280 Vacuum chamber
SZSB-120 Temperature circulation chamber
SZSB-128 Vibration test instrument
SZSB-082 Shock test instrument
SZSB-281 Battery anti-explosion chamber

SZSB-077 DC regulated power supply
SZSB-198 Battery extrusion needling machine
SZSB-125 Electronic balance
SZSB-090 Digital multimeter
SZSB-185 Thermoelectric pair

HIGHER POWER TECHNOLOGY CO.,LIMITED

IX、 DATA

1. Altitude simulation

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	24.500	4.17	24.500	4.17	0.000	0.00	N
N2	24.442	4.17	24.442	4.17	0.000	0.00	N
N3	24.502	4.17	24.503	4.16	0.000	0.24	N
N4	24.248	4.17	24.248	4.17	0.000	0.00	N
C1	24.412	4.17	24.411	4.17	0.006	0.00	N
C2	24.478	4.17	24.478	4.17	0.000	0.00	N
C3	24.460	4.17	24.460	4.17	0.000	0.00	N
C4	24.568	4.17	24.568	4.17	0.000	0.00	N

2. Thermal test

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	24.500	4.17	24.495	4.12	0.030	1.20	N
N2	24.442	4.17	24.436	4.13	0.036	0.96	N
N3	24.502	4.16	24.508	4.13	0.031	0.72	N
N4	24.248	4.17	24.244	4.12	0.025	1.20	N
C1	24.411	4.17	24.407	4.13	0.024	0.96	N
C2	24.356	4.17	24.351	4.13	0.031	0.96	N
C3	24.460	4.17	24.455	4.12	0.030	1.20	N
C4	24.568	4.17	24.564	4.13	0.025	0.96	N

HIGHER POWER TECHNOLOGY CO.,LIMITED

3. Vibration

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	24.495	4.12	24.495	4.12	0.000	0.00	N
N2	24.436	4.13	24.436	4.12	0.000	0.24	N
N3	24.308	4.13	24.307	4.13	0.006	0.00	N
N4	24.244	4.12	24.244	4.12	0.000	0.00	N
C1	24.407	4.13	24.407	4.13	0.000	0.00	N
C2	24.351	4.13	24.350	4.12	0.006	0.24	N
C3	24.455	4.12	24.455	4.12	0.000	0.00	N
C4	24.564	4.13	24.563	4.13	0.006	0.00	N

4. Shock

No.	Pre-test		After test		Mass loss (%)	Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	24.495	4.12	24..995	4.12	0.000	0.00	N
N2	24.436	4.12	24.436	4.12	0.000	0.00	N
N3	24.307	4.13	24.307	4.12	0.000	0.24	N
N4	24.244	4.12	24.243	4.12	0.006	0.00	N
C1	24.407	4.13	24.407	4.12	0.000	0.24	N
C2	24.350	4.12	24.350	4.12	0.000	0.00	N
C3	24.455	4.12	24.454	4.12	0.006	0.00	N
C4	24.563	4.13	24.563	4.12	0.000	0.24	N

HIGHER POWER TECHNOLOGY CO.,LIMITED

5. External short circuit

No.	Peak temperature (°C)	Whether disassembly, rupture, fire (Y/N)
N1	55	N
N2	56	N
N3	59	N
N4	55	N
C1	57	N
C2	55	N
C3	58	N
C4	56	N

6. Crush

No.	Peak temperature (°C)	Whether disassembly, fire (Y/N)
N9	25	N
N10	26	N
N11	26	N
N12	25	N
N13	26	N

7. Overcharge

No.	Whether disassembly, fire (Y/N)
N5	N
N6	N
N7	N
N8	N
C5	N
C6	N
C7	N
C8	N

8. Forced discharge

N/A (Not applicable)